

# EVA

To enquire, Visit: [www.jitsy.in](http://www.jitsy.in)

## EVA for extrusion coating

### Application

Coating, BOPP coating

[www.jitsy.in](http://www.jitsy.in)

[www.jitsy.in](http://www.jitsy.in)

[www.jitsy.in](http://www.jitsy.in)

### Characteristics

Excellent transparency, Excellent extrusion processability and productivity, Neck-in, Adhesive

### Physical properties

Item	Test Method	Unit	Typical Value
Melt index	ASTM D1238 (190°C, 2.16kg )	g/10min	15
Density	ASTM D1505	g/cm³	0.940
VA content	HTC Method	%	18
Melt temperature	HTC Method	°C	83
Tensile strength (at break)	ASTM D638	kg/cm²	130
Elongation (at break)	ASTM D638	%	>600
Vicat softening point	ASTM D1525	°C	56
Brittleness temperature	ASTM D746	°C	<-70

Note) Data shown above are representative values for reference purposes only, and not to be construed as specifications.

### Processing conditions

Item	Unit	Typical value
Hopper unit	°C	Room temp
Barrel temperature	°C	130 ~ 240
Extrusion temperature	°C	220 ~ 240
Temperature of Die unit	°C	230 ~ 240

※ Optimal extrusion molding conditions may vary depending on facility specifications such as screw type, die structure, and extrusion amount, and please use the above figures as reference.

### Certification

Hanwha TotalEnergies Petrochemical E182L satisfies the 21 CFR 177.1350 regulations, the food packaging standards of the U.S. Food and Drug Administration(FDA). For further inquiries, please contact Customer Technical Service.

## Contact information

To enquire, Visit: [www.jitsy.in](http://www.jitsy.in)

Hanwha TotalEnergies Petrochemical Co., Ltd.  
[www.htpchem.com](http://www.htpchem.com)

Sales Office  
(04525) 16F, Hanwha Finance Plaza Bld, 92,  
Sejong-daero, Jung-gu, Seoul, Republic of Korea

Customer Technical Service  
(31900) 103, Dokgot 2-ro, Daesan-eup, Seosan-si,  
Chungcheongnam-do, Republic of Korea  
T. 041-660-6143 F. 041-660-6189

## Disclaimer

This document is copyrighted by Hanwha TotalEnergies Petrochemical. All information is for reference only and is not the specifications of the final product. Customers should make their own judgments as to whether our products and information serve a particular purpose and what regulations apply to customers' use of such products. Hanwha TotalEnergies Petrochemical is not responsible or obligated for the contents of this document. Hanwha TotalEnergies Petrochemical provides no warranties of any kind, either express or implied (such as merchantability and or fitness for a particular purpose, etc.) with respect to any information contained in this material. Hanwha TotalEnergies Petrochemical may arbitrarily change the contents of this material without prior notice.