



Provisional Technical Datasheet

CE06NR Polysure PP Impact Copolymer Caps and Closure

To enquire, Visit: www.jitsy.in

Product Characteristics:

Polysure CE06NR is a Polypropylene Impact Copolymer, produced by latest Spheripol – II Technology & primarily suitable for high speed Continuous Compression Molding & Injection molding processes. CE06NR is a nucleated grade and it offers superior organoleptic properties, enhanced stiffness, high slip and low cycle time for high productivity.

Recommended Applications:

Cap & Closures, Lids, Housewares, Toys

Typical Properties:

Sr. No.	Property	Test Method	Unit	Value*
1	Melt Flow Index (230°C & 2.16 kg)	ASTM D1238	g/10 min	6
2	Tensile Strength at Yield, Type I Specimen	ASTM D638 (50 mm / min)	MPa	31
3	Tensile Elongation at Yield, Type I Specimen		%	7
4	Flexural Modulus (1% Secant)	ASTM D790A	MPa	1450
5	Notched Izod Impact Strength (23°C)	ASTM D256A	J/m	80
6	Vicat Softening Point (10 N)	ASTM D1525	°C	150
7	Heat Deflection Temperature (0.455 MPa)	ASTM D648	°C	115

*All the mechanical properties are tested on Injection molded Test Specimen, prepared in accordance with ASTM D4101

Processing Guidelines:

- Processing Temperature: 190 - 230°C

Storage & Handling:

Bags should be stored in dry & dust free environment at temperature below 50°C and Prevent from direct exposure to sunlight & heat to avoid quality deterioration.

Regulatory Requirements:

CE06NR to be manufactured complying the requirements specified in IS 10910 on “Specification for Polypropylene & its Copolymers for safe use in contact with Foodstuff, Pharmaceutical & Drinking water”. Furthermore, the Additives added in this grade formulation compiles to the “Positive list of constituents for Polypropylene, Polyethylene and their Copolymers for its safe use in contact with Foodstuffs & Pharmaceuticals”, as laid down under IS 16738:2018. In general, the additives & constituents used in the grade are in line with requirement laid down under FDA: CFR Title 21,177.1520, Olefin Polymers.

To enquire, Visit: www.jitsy.in

Updated as of May 2021

Disclaimer: The information & data presented herein are typical values & should not be considered as specification and may be used as guideline only. HMEL does not undertake any responsibility for any outcome or results from the adoption or replication of the above-mentioned data & information there on for possible use for various applications. HMEL reserves the right to change the information & data without any prior notice or information. The user will solely be responsible for any process/product usage.

HPCL-Mittal Energy Limited (HMEL), INOX Tower, Plot No.17, Sector-16A, Noida – 201301 (U.P), India. Tel: 0120-4634500. Corporate Site: www.hmel.in