



**MARPOL**  
**EVA 802**  
 Ethylene Vinyl Acetate

# PRODUCT DATA SHEET

PROPERTY	VALUE	ASTM
<b>Melt Index, 190°C/ 2.16kg (g/10 min)</b> To buy, visit us at <a href="http://www.jitsy.in">www.jitsy.in</a>	<b>2.0</b>	<b>D 1238</b>
<b>Vinyl Acetate Content (%)</b>	<b>8.7</b>	
<b>Density (g/cm<sup>3</sup>)</b>	<b>.930</b>	<b>D 1505</b>
<b>Vicat Softening Point (°F)</b>	<b>178</b>	<b>D 1525</b>
<b>Tensile Strength at Break (psi)</b>	<b>MD 4400</b> <b>TD 4000</b>	<b>D 882</b>
<b>Elongation at Break (%)</b>	<b>MD 330</b> <b>TD 660</b>	<b>D 882</b>
<b>1% Secant Modulus (psi)</b>	<b>MD 16000</b> <b>TD 17000</b>	<b>D 882</b>
<b>Dart Drop Impact (g)</b>	<b>250</b>	<b>D 1709A</b>
<b>Elmendorf Tear Strength (g)</b>	<b>150</b>	<b>D 1922</b>
<b>Gloss (45°)</b>	<b>88</b>	<b>D 2457</b>
<b>Haze (%)</b>	<b>1.5</b>	<b>D 1003</b>

To buy, visit us at [www.jitsy.in](http://www.jitsy.in)

MARPOL® EVA 802 is an 8.7% vinyl acetate copolymer film resin with excellent impact strength and heat sealability.

**Recommended Applications:** Films for meat packaging and primal meat bags

This information, to our knowledge, is believed to be correct. The use of this product in its actual conditions are beyond our control and satisfactory results for this product is the customer's sole responsibility.