

Provisional Technical Datasheet

EI02N



Polypropylene Impact Co Polymer

Extrusion Products

To enquire, Visit: www.jitsy.in

Product Description:

PP Block Co polymer EI02N is a heterophasic natural colored & nucleated grade produced with the latest Ineos Gas Phase polymerization

Technology exhibiting following features:

- ✓ Higher Stiffness
- ✓ Nucleated Grade

PP Block Co Polymer EI02N is recommended for extrusion applications such as:

- ✓ Food Service Trays
- ✓ Containers
- ✓ Rigid Packaging

Typical Properties:

Sr. No.			Units	Values*
Physical Properties				
1	Melt Flow Index (230°C & 2.16 kg)	ASTM D1238	g / 10 min	1.9
2	Density (23 °C)	ASTM D 1505	Gm/cm ³	0.90
Mechanical Properties				
3	Tensile Strength @ Yield (50mm / min)	ASTM D 638	MPa	33
4	Elongation @ Break (50mm / min)	ASTM D 638	%	>25
5	Flexural Modulus (1.3 mm/min)	ASTM D790A	MPa	1650
6	Notch Izod Impact Strength (@ 23°C)	ASTM D 256	J/m	NB
7	Hardness (Rockwell)	ASTM D 785	R Scale	97
Thermal Properties				
8	Heat Deflection Temperature (0.46N/m ²)	ASTM D648	°C	115

* Mechanical Properties tested on Injection molded specimen prepared in accordance with ASTM D 4101 and conditioned as per ASTM D 618

* Typical Values and not to be taken as specifications, values may change without any prior notice.

Recommended Processing Temperature: 180 – 230 °C

To enquire, Visit: www.jitsy.in

Disclaimer: OPAL assumes no liability whatsoever in respect of application, processing or any use made of the afore - mentioned information or products, or any consequence thereof. The user undertakes all liability in respect of the application, processing or use of the afore - mentioned information or product, whose quality and other properties he shall verify, or any consequence thereof. No liability whatsoever shall be attached to any of the OPAL companies for any infringement of the rights owned or controlled by a third party in intellectual, industrial or other property by reason of application, processing or use of the afore-mentioned information or products by the user.

Contact: ONGC Petro Additions Ltd., Polymer Marketing Group: 1st Floor, Omkara Complex, Sai Chowkdi, Manjalpur, Vadodara 390011, Gujarat, India
Telephone: +91 265 6192600, Fax: +91 265 6192666, Corporate Site: www.opalindia.in PARC/2016/03 - 00