



Technical Datasheet

F10SR Polypropylene Homopolymer

TQPP Films

Product Characteristics:

Polysure F10SR is Polypropylene Homopolymer, produced by Latest Novolen Technology & Primarily suitable for Tubular water quench film applications. F10SR combines exceptional processability with superior Slip, Anti Blocking properties, Excellent Clarity and Gloss.

Recommended Applications:

F10SR is recommended to Process Tubular Quenched (TQ) Film for packaging foodstuffs and garments, snack food, grocery & general purpose packaging

Typical Properties:

To buy, visit us at www.jitsy.in

Sr. No.	Property	Test Method	Unit	Value*
1	Melt Flow Index (230°C & 2.16 kg)	ASTM D1238	g/10 min	10.5
2	Tensile Strength @ Yield (50mm / min)	ASTM D638	MPa	33
3	Tensile Elongation @ Yield (50mm / min)	ASTM D638	%	10
4	Flexural Modulus (1% Secant)	ASTM D790A	MPa	1300
5	Notch Izod Impact Strength (23°C)	ASTM D256	J/m	35
6	Vicat Softening Point (10N)	ASTM D1525	°C	153
7	Heat Deflection Temperature (0.455 MPa)	ASTM D648	°C	95

*All the mechanical properties are tested on Injection molded Test Specimen, prepared in accordance with ASTM D 4101

Processing Guidelines:

- Barrel Temperature : 180 - 230°C
- Die Temperature : 190 - 210°C

Storage & Handling:

Bags should be stored in dry & dust free environment at temperature below 50°C and Prevent from direct exposure to sunlight & heat to avoid quality deterioration.

Regulatory Requirements:

F10SR is manufactured complying the requirements specified in IS 10910 on "Specification for Polypropylene & its Copolymers for safe use in contact with Foodstuff, Pharmaceutical & Drinking water". Furthermore the Additives added in this grade formulation compiles to the "Positive list of constituents of Polypropylene and its Copolymers in contact with Foodstuff, Pharmaceutical & Drinking water' as laid down under IS 10909. In general the additives & constituents used in the grade are in line with requirement laid down under FDA: CFR Title 21,177.1520, Olefin Polymers.

Updated as of September 2023

To buy, visit us at www.jitsy.in

Disclaimer: The information & data presented herein are typical values & should not be considered as specification and may be used as guideline only. HMEL does not undertake any responsibility for any outcome or results from the adoption or replication of the above mentioned data & information there on for possible use for various applications. HMEL reserves the right to change the information & data without any prior notice or information. The user will solely be responsible for any process/product usage.

HPCL-Mittal Energy Limited (HMEL), INOX Tower, Plot No.17, Sector-16A, Noida – 201301 (U.P), India. Tel: 0120-4634500. Corporate Site: www.hmel.in