

TECHNICAL DATA SHEET

P5200

P5200 is a HDPE pipe grade produced by Mitsui CX Process

P5200 combines excellent processability with good creep resistance, ESCR and mechanical properties

P5200 is recommended for **PE 63** compliant pressure pipes

Need pricing, availability, or technical support? Explore our website - www.jitsy.in

BIS Designation Code: IS 7328-3B-PB-EXTA

| Property | Test Method | Unit | Nominal Value |
|---|---|-------------------|---------------|
| Melt Flow Index (2.16 kg, 190°C) | ASTM D1238, IS 13360 (Part 4/Sec 1) | g/10 min | 0.20 |
| Melt Flow Index (5 kg, 190°C) | | g/10 min | 0.90 |
| Melt Flow Index (21.6 kg, 190°C) | | g/10 min | 22 |
| Density (23°C, Annealed) | ASTM D1505, IS 13360 (Part 3/Sec 11) | g/cm ³ | 0.950 |
| Density (23°C, Annealed) | JIS MCI HZ-F-109 | g/cm ³ | 0.954 |
| Density (27°C, Annealed) | IS 4984 | g/cm ³ | 0.948 |
| Physical Property | | | |
| Tensile Strength at Yield | ASTM D638 (50 mm/min) | MPa | 25 |
| Elongation at Yield | | % | 8 |
| Tensile Strength at Break | | MPa | 38 |
| Elongation at Break | | % | 900 |
| Notched Izod Impact Strength (23°C) | ASTM D256A | J/m | 175 |
| Flexural Modulus | ASTM D790A | MPa | 1000 |
| Hardness | ASTM D2240 | Shore D | 65 |
| ESCR (F ₅₀ , 10% Igepal soln. v/v) | ASTM D1693B | Hr | >1000 |
| Vicat Softening Point (10 N) | ASTM D1525 | °C | 123 |
| Heat Deflection Temperature (0.455 MPa) | ASTM D648 | °C | 64 |
| DSC Melting Temperature | ASTM D3418 | °C | 131 |
| Oxidative Induction Time | ASTM D3895 | min | >30 |

Need pricing, availability, or technical support? Explore our website - www.jitsy.in



Halene – H*

| Suggested Processing Conditions | |
|---------------------------------|--------------|
| Barrel Temperature | 150 – 180 °C |
| Die Temperature | 170 – 180 °C |

*Halene H is the registered trademark of High-Density Polyethylene of Haldia Petrochemicals Limited

Mechanical Properties are on specimens from Compression Moulded Sheet prepared in accordance with ASTM D4703

This grade meets the requirements of:

IS 7328:2020 Specification for Polyethylene Material for Moulding and Extrusion

IS 16738:2018 Positive List of Constituents for Polypropylene, Polyethylene and their Copolymers for its Safe Use in Contact with Foodstuffs and Pharmaceuticals

IS 10146 for use in contact with foodstuffs, pharmaceuticals, and drinking water.

This product is not recommended for manufacturing of Single Use Plastic (SUP) items listed under Plastics Waste Management (PWM) Rule 2016 and its latest amendment.

The information and data presented herein are typical values of representative samples and should not be construed as specification or tested values of supplied product. Prior to use, buyer shall ensure independently through tests and trials, that HPL products can be handled and used by them legally, safely, and suitably for their intended operation and end-use application. No warranty or guarantee expressed or implied is made regarding performance or otherwise. In no event shall HPL be liable for any damage, loss or injury directly or indirectly suffered as a result of use of product or information provided herein. The information & data contained herein are reliable to the best of our knowledge on the date of release of the document and is subject to change without prior intimation based on research & development work undertaken by HPL

Compliance Certificates & MSDS are available on request.

Visit us at www.haldia Petrochemicals.com

Need pricing, availability, or technical support? Explore our website - www.jitsy.in