



040R40A

Linear Low Density Polyethylene

Rotational Molding

Need pricing, availability, or technical support? Explore our website - www.jitsy.in

Product Description:

LLDPE 040R40A is a medium density polyethylene made with state of the art Nova Chemical's Sclairtech solution polymerization technology. It is a natural colored polymer with very good Impact Stiffness balance and Hardness.

Recommended Applications:

LLDPE 040R40A is recommended for following applications:

- Medium and Large Tanks
- Manholes and Chambers
- Septic tanks

Typical Properties:

Tested Properties	Test Method	UOM	Values*
Resin Properties			
Melt Flow Index (190°C & 2.16 Kg)	ASTM D 1238	gm/10 min	3.6
Density @ 23°C	ASTM D 1505	gm/cm ³	0.940
Mechanical Properties			
Tensile Strength @ Yield	ASTM D 638	MPa	21
Elongation at Break	ASTM D 638	%	600
Notched Izod Impact Strength	ASTM D 256	J/m	220
Flexural Modulus	ASTM D790	Mpa	900
Hardness	ASTM D 2240	Shore D	58
Thermal Properties			
Vicat Softening Point (10N)	ASTM D1525	°C	118

*Typical values not to be construed as specification limits. Values may change without any prior notice.

* Mechanical Properties tested on Injection Molded test specimens.

Recommended Processing Temperature: 170 – 215 °C

Packaging Information:

This material is packed and available in raffia bags with net content of 25.0 Kg only. The raffia bags used conforms to the minimum strength requirements of BIS, however, customer shall take due care while handling the bag. Prolonged exposure of these bags to sunlight may deteriorate the bag's performance and cause spillage and wastage. IOCL does not warrant loss of material due to poor material handling practices.


Regulatory Information:

LLDPE 040R40A shall meet Specification for Polyethylene for safe use in contact with Foodstuff, Pharmaceuticals and Drinking water" as per IS: 10146-1982. It also confirms to the positive list of constituents as per IS: 10141-1982. The grade and Additives incorporated shall meet with FDA: CFR Title21, 177.1520, Olefin Polymers.

Storage & Handling:

Prevent LLDPE Material from direct exposure to sunlight & heat to avoid quality deterioration. The storage location should be dry, dust free and the storage temperature should no exceed 50°C. Non - compliance to these precautionary measures can lead to degradation of the product causing color changes, odor and inadequate product performance. It is advised to process LLDPE material within 06 months of delivery.

Disclaimer: IOCL assumes no liability whatsoever in respect of application, processing or any use made of the aforementioned information or products, or any consequence thereof. No liability whatsoever shall attached to any of the IOCL companies for any infringement of the rights owned or controlled by a third party in intellectual, industrial or other property by

 <p>Registered Office Address → G-9, Aiyavar Jung Marg, Bandra (East), Mumbai – 400051 Maharashtra, India.</p>	<p>Contact Address → Product Application and Development Center (PADC), Near Panipat Naphtha Cracker Complex, Village – Bajattan, Panipat – 132140, Haryana, India</p>	<p>Contact Details → Tel : +91-180-2526705/2526708 Fax : +91-180-2526689 Web : https://propel.indianoil.in</p>
--	---	---

Provisional Technical Datasheet