

DOW-MITSUI POLYCHEMICALS CO., LTD.

Shiodome City Center
5-2, Higashi-Shimbashi 1-chome
Minato-ku, Tokyo 105-7117, Japan

TEL: 81-3-6253-4006
FAX: 81-3-6253-4262

EVAFLEX™ V421

Need pricing, availability, or technical support? Explore our website - www.jitsy.in

Property	Test Method	Units	V421
VA Content	JIS K7192	wt%	28
MFR	JIS K7210	g/10min	4
Density	JIS K7112	Kg/m ³	950
Tensile Strength	JIS K7161	MPa	25
Elongation	JIS K7161	%	800
Stiffness	JIS K7106	MPa	15
Hardness(Shore A)	JIS K7215	Degree	82
Vicat Softening Point	JIS K7206	°C	42
Melting Point	JIS K7121	°C	73

The data shown are typical values and should not be used for specifications.



Dow-Mitsui Polychemicals

A JOINT VENTURE

Need pricing, availability, or technical support? Explore our website - www.jitsy.in